

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A

69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 27.11.2024

TECHNICAL DATA SHEET

AEROSOL ISOLATOR/SEALER PRIMER

Article number: 26723

Colour: beige

Intended use: Car refinishing product/ Primer

miended door

Nitro-acrylic primer, which efficiently protects old, solvent-sensitive paint coats (e.g. thermoplastic coatings, coatings based on alkyd resins, etc.) from lifting or blooding when they are overcasted

lifting or bleeding when they are overcoated.

quick drying

high coverage

good adhesion

improves adhesion for the top-coat

Fields of application:

ferrous surface
non-ferrous surfaces
wood

TECHNICAL CHARACTERISTICS

Base: nitro-acrylic Smell: characteristic

General characteristics:

Consumption: 0.8 - 1.2 m² (4 crossed layers)

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +15 °C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers
- Beforehand, mask the parts that shouldn't be painted



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG

GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

- Degrease the surface
 - Wear a respirator (type A2/P3 is recommended)
 - The aerosol should have room temperature
 - Before use, shake the aerosol for 2 min and spray a sample
 - Distance to the surface should be approximately 20 25 cm
 - If the scratches or imperfections are deep, apply more coats, waiting for 15 min between applications
 - To get even coverage of the product, we recommend shaking the can between layers
 - Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dry to touch	Completely dry
Object temperature 20 °C	10 - 15 min	24 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

ATTENTION

DO NOT DEGREASE the surface after applying the Isolator primer, as this is a one-component, solvent sensitive product, - the primer can be removed with a degreaser/thinner.

VOC regulation:

EU limit value: Category B/e 840 g/l This product contains max. 632 g/l

Shelf life:

120 months, if stored in tightly closed original containers

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.