



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

**TECHNICAL DATA SHEET** 

Revision date: 14.06.2024

## SOFTLIGHT PUTTY

Article number: 15554, 15555, 15557

Colour: light beige

Intended use: Car refinishing product/ Knife filler/ Surfacer

General characteristics: Softlight putty is a creamy, lightweight putty

Softlight putty is a creamy, lightweight putty for smaller dents and scratches. Thanks to micro-fine fillers it is possible to achieve a very smooth, even surface. The putty is easy to sand because of its flexible and constant texture.

high elasticity

poreless application over large surfaces

good stability on vertical surfaces

## Fields of application:

zinc

■ iron

aluminium and its alloys

■ GRP

steel

galvanized steel

#### TECHNICAL CHARACTERISTICS

Basis: polyester resin

Density at 20°C: putty 1.8 g/cm<sup>3</sup>

hardener 1.15 g/cm<sup>3</sup>

#### PAINTING PREPARATION PROCESS

Hardener: Hardener P

Mixing ratio (by weight): 100: 2

Do not use more than 3% of hardener P! Under- or overdosage of hardener may cause spotting in the

finishing paint layer.

Pot life at 20 °C: 4 - 5 min

## APPLICATION PROCESS



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Before use, carefully read and observe the warning texts on the label!

#### Processing conditions:

Please only use in an adequately ventilated environment with an ample supply of fresh air. Processing temperature should be at least +12 °C and max. air humidity should not exceed 80%. Polyester-based body filler does not cure at a temperature of below +10 °C.

Drying	Sandable
Object temperature 20 °C	20 - 30 min
Object temperature 60 °C	10 - 15 min

## Processing tips

- The substrate must be clean, dry and free from grease.
- Sand surfaces thoroughly. Remove loose/old paintwork and priming coats.
- Clean and degrease the whole surface to be painted before every operation.
- De-rust defective spots to bare metal and dry sand with sanding paper P80/150.
- Mix well the putty material with the hardener.
- After drying, use sanding paper P120/240 for dry sanding.
- Sand the entire surface with dry sandpaper P240/360 to a matt finish before applying filler.
- In case of filling work on non-ferrous metals (e.g. aluminium, zinced surfaces) it is advised to apply a priming coat of Chamäleon Epoxy primer to ensure an optimal adhesion before applying the putty.
- Putty can only be dry sanded.

#### **ATTENTION**

- Do not apply on thermoplastic or acid products (wash-primer).
- Do not overcoat with topcoats without having isolated the surface with Chamäleon 1K or 2K primer.
- Do not return mixed material into the can.
- Clean tools immediately after use, if necessary, with a nitro thinner.

# **VOC** regulation:

EU limit value: Category B/b 250 g/l This product contains max. 15 g/l VOC

### Shelf life:

18 months, if stored in tightly closed original containers

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.