

**TECHNICAL DATA SHEET***Revision date: 08.05.2025***AEROSOL RUST CONVERTER PRIMER**

<b>Article number:</b>	<b>26060</b>
<b>Colour:</b>	transparent
<b>Intended use:</b>	Car refinishing product/ Protective coating
<b>General characteristics:</b>	<p>Rust converter primer fights rust and forms a dark grey almost black protective coating after drying. In addition, the epoxy resin layer seals the converted metal surface and cures to an excellent priming coat after 12 to 24 hours.</p> <ul style="list-style-type: none"><li>▪ rust is chemically converted, treated surfaces turn black</li><li>▪ fights rust and protects against new corrosion</li><li>▪ long lasting corrosion protection and priming in one operation</li></ul> <p><b>Substrates:</b></p> <ul style="list-style-type: none"><li>▪ steel</li><li>▪ galvanized steel</li></ul>

**TECHNICAL CHARACTERISTICS**

**Base:** epoxy-resin  
**Smell:** characteristic

**APPLICATION PROCESS**

Before use, carefully read and observe the warning texts on the label!

**Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +10 °C to +25 °C and max. air humidity should not exceed 80%.

**Processing tips:**

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers.
- Use a suitable abrasive method (e.g. wire brush) to remove loose rust



- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Distance to the surface should be approximately 20 - 25 cm
- Apply in 3 - 4 coats or until the product has penetrated the residual rust well
- Keep a flash off time 3 - 5 min between each spray pass
- Apply Rust converter primer until the residual rust is sufficiently well penetrated. A dark grey to black discolouration of the corroded surfaces after drying serves as a visual control
- If there is still no uniform dark discolouration or residual rust is still visible, repeat the application procedure
- If necessary, may be re-coated with polyester-based putties after 24 h drying
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Set to touch	Re-coatable
Object temperature 20 °C	12 - 24 h	24 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 800 g/l VOC

### Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding Safety Data Sheet.