

**TECHNICAL DATA SHEET***Revision date: 10.04.2025***AEROSOL UNDERBODY PROTECTION**

|                                 |  |
|---------------------------------|--|
| <b>Article number:</b>          | <b>37014 (white), 37024 (grey), 37034 (black)</b>  |
| <b>Colour:</b>                  | white, grey, black   |
| <b>Intended use:</b>            | Car refinishing/ Anticorrosion product   |
| <b>General characteristics:</b> | High quality stone chip and corrosion protection for the underside and wheel wells of cars. The product has very good insulating and sound dampening properties. <ul style="list-style-type: none"><li>▪ re-sprayable with all lacquer systems</li><li>▪ remains flexible</li><li>▪ very good adhesion</li><li>▪ resistant to weather influences</li><li>▪ resistant to weak acids and bases</li></ul> |

**TECHNICAL CHARACTERISTICS****Base:** synthetic resin**Smell:** characteristic**Consumption:** 1.0 - 1.5 m<sup>2</sup> (500 ml)**APPLICATION PROCESS**

Before use, carefully read and observe the warning texts on the label!

**Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12 °C to +25 °C and max. air humidity should not exceed 80%.

**Processing tips:**

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers.
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, test the compatibility of the surface

- Before use, shake the aerosol for 2 min and spray a sample
- Distance to the surface should be approx. 25 - 30 cm
- Apply in several layers
- Keep a flash off time 5 - 10 min between each spray pass (depending on the layer thickness)
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

| Drying                   | Dust free | Set to touch | Re-coatable |
|--------------------------|-----------|--------------|-------------|
| Object temperature 20 °C | 30 min    | 1 h          | 2 h         |

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 579.6 g/l VOC

### Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding Safety Data Sheet.