

**TECHNICAL DATA SHEET**

Revision date: 10.04.2025

AEROSOL CONTACT ADHESIVE

Article number:	26803												
Colour:	white-transparent												
Intended use:	Car refinishing product/ Contact adhesive												
General characteristics:	<p>Multi-purpose contact adhesive with a synthetic rubber base engineered for bonding large surfaces with durable, long-lasting adhesion. Features an adjustable valve for precise control of spray rate.</p> <ul style="list-style-type: none">▪ quick and reliable to use▪ fast drying▪ user-friendly <p>Substrates:</p> <table><tr><td>▪ carpet</td><td>▪ rubber</td><td>▪ foam rubber</td></tr><tr><td>▪ cork</td><td>▪ paper</td><td>▪ cardboard</td></tr><tr><td>▪ textiles</td><td>▪ wood</td><td>▪ leather</td></tr><tr><td>▪ metal</td><td>▪ leather</td><td>▪ various types of plastic</td></tr></table>	▪ carpet	▪ rubber	▪ foam rubber	▪ cork	▪ paper	▪ cardboard	▪ textiles	▪ wood	▪ leather	▪ metal	▪ leather	▪ various types of plastic
▪ carpet	▪ rubber	▪ foam rubber											
▪ cork	▪ paper	▪ cardboard											
▪ textiles	▪ wood	▪ leather											
▪ metal	▪ leather	▪ various types of plastic											

TECHNICAL CHARACTERISTICS**Base:** synthetic resin**Smell:** characteristic**Consumption:** 1.0 - 1.5m² (500 ml)**Nozzle type:** fan variable**APPLICATION PROCESS**

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12 °C to +25 °C and max. air humidity should not exceed 80%.



Processing tips:

- The substrate must be clean, dry, free from rust and grease
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min
- Before use, test the compatibility of the surface
- Distance to the surface should be 25 - 30 cm (more for polystyrene foam)
- **For long-lasting adhesion:**
apply a thick layer of adhesive to both parts and wait for 15 - 20 min to dry, after drying time, press the surfaces together and maintain the pressure for a certain period of time
- **For temporary adhesion:**
apply a thin, even layer to both sides of the substrate to be bonded and press them together after 5 - 10 min
- When treating porous surfaces, apply several layers
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 586.1 g/l VOC

Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.