

TECHNICAL DATA SHEET

Revision date: 30.04.2025

AEROSOL HEAT RESISTANT

Article number:	26601 (black), 26602 (silver)
Colour:	black, silver
Intended use:	Car refinishing product/ Paint
General characteristics:	High quality lacquer designed for both treated and untreated surfaces exposed to very high temperatures. <ul style="list-style-type: none">▪ excellent adhesion▪ resistant to petrol, chemicals and weather influences▪ heat resistant Fields of application: <ul style="list-style-type: none">▪ steel▪ iron▪ aluminum▪ exhaust pipes▪ grills, stoves▪ chimneys▪ ceramics▪ concrete▪ glass

TECHNICAL CHARACTERISTICS

Base: silicone resin**Smell:** characteristic**Consumption:** 1.25 - 1.75 m² (400 ml)**Temperature resistant:** up to 650°C

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12°C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers.
- Beforehand, mask the parts that shouldn't be painted



- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Apply in several thin layers
- Before applying the next layer, again shake the aerosol
- Distance to the surface should be 25 - 30 cm
- Allow to dry at room temperature for 1h
- Then, heat for 30 to 60 min (200°C) in order to harden the paint layer
- Smoke may be produced during the lacquer curing process
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

ATTENTION:

This product contains silicone. Do not use this product in areas where silicone may cause problems!

Drying	Dust free	Set to touch	Completely dry
Object temperature 20 °C	5 - 10 min	10 - 15 min	30 - 60 min

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l

The art. 26601 contains max. 612.6 g/l VOC

The art. 26602 contains max. 670.1 g/l VOC

Shelf life:

120 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.