

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 13.05.2024

**TECHNICAL DATA SHEET** 

**LEATHER PAINT** 

Article number: 26801, 26808, 26809

Colour: black, beige, grey

Intended use: Car refinishing product/ Colour spray for smooth leather

General characteristics: High quality leather paint to repair and embellish parts of leather, vinyl and artificial leather.

- Lasting colour and lasting gloss
- Elastic
- Excellent adhesion
- Maintains the original structure Surfaces:
- vinyl
- leather
- artificial leather

## **TECHNICAL CHARACTERISTICS:**

Basis of binder: nitrocellulose binder Temperature resistance: to 50 °C

Consumption: 1-2 m<sup>2</sup>

## APPLICATION PROCESS

#### Processing conditions:

VAT NO. / UST-ID NR.: DE231468544 EORI NO. / EORI NR.: DE6029442

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +12 °C and max. air humidity should not exceed 80%.

Before use, carefully read the directions on the packaging and act accordingly.

- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- The aerosol should have room temperature. Best processing temperature 15 to 25°C.



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

- Before use, shake the aerosol for 2 minutes and spray a sample.
- Distance to the surface to be treated approx. 25 30 cm.
- Apply the vinyl spray in several thin layers.
- Before applying the next layer, again shake the aerosol.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approx. 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

# Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Drying	dust free	Set to touch	hardened/resprayable
Air drying 20 °C	5-10 min	10-20 min	after 2 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

## **VOC** regulation:

EU limit value: Category B/e 840 g/l This product contains max. 682.2 g/l

## Shelf life:

120 months, if stored in tightly closed original containers

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.