



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 11.01.2024

## **TECHNICAL DATA SHEET**

## HS 2K FAST & PERFECT EXPRESS CLEAR COAT

Article number: 11805, 11808

Colour: transparent

Intended use: Car refinishing product/ Clear coating material, Varnish

Substrates: Basecoat

General characteristics: 2K High quality Fast & Perfect HS express clear coat

for fast and economic car refinishing (express technology), especially in case of oven drying. It is also suitable for spot repair. This product provides excellent resistance against environmental and weathering conditions as well as yellowing and offers durable gloss

retention.

#### PAINTING PREPARATION PROCESS

Hardener: Chamäleon HS Hardener 280

Dilution: without thinner
Mixing ratio (by volume): 2:1
Mixing ratio (by weight):

No thinner is added. Do not zero the scale when mixing.

Clear coat, g	Hardener, g	Total weight, g	Mixture quantity, ml
67	35	102	100
134	69	203	200
201	104	305	300
268	138	406	400
335	173	508	500
402	207	609	600
469	242	<i>7</i> 11	700
536	276	812	800





CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG

FON 0049 (0) 6221 - 520 440

FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

603	311	914	900
670	345	1015	1000

Spraying viscosity 4 mm DIN (20 °C): 17 - 19 s

Pot life at 20 °C: 1 - 1.5 h

#### APPLICATION PROCESS

### Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least  $+12~^{\circ}\text{C}$  and max. air humidity should not exceed 80%.

Application method	Pressure	Nozzle
Gravity spray gun	2.0 - 2.5 bar	1.2 - 1.3 mm
HVLP	2.0 - 2.5 bar	1.2 - 1.3 mm

Spraying operations	DFT	Consumption
1,5	40 - 60 μm	9.0 - 10.0 m <sup>2</sup> /l

Flash-off time	Between the coatings	Before the oven drying	
	3 - 5 min	10 - 15 min	

Drying	Dust free	Set to touch	Full hardness
Object temperature 20 °C	15 - 20 min	1 - 2 h	6 h
Object temperature 60 °C	-	15 min	15 min
IR-drying shortwave*	8 min		
IR-drying mediumwave*	10 - 15 min		

<sup>\*</sup>During IR-drying the object temperature should not exceed 60 – 70 °C

## Polishing:

After full hardness time, recommended Chamäleon polishing compounds LASER

# **VOC** regulation:

EU limit value: Category B/d 420 g/l This product contains max. 420 g/I VOC

### Shelf life:

36 months, if stored in tightly closed original containers



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG

FON 0049 (0) 6221 - 520 440

MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.