



CHAMAI

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449 MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

Revision date: 16.07.2024

1K PAINT BLACK MATT 1K PAINT SILVER RAL 9006

Article number:	50010, 50020 black matt, silver RAL 9006		
Colour:			
Intended use:	Car refinishing product/ Basecoat		
Substrates:	Primer		
General characteristics:	Fast drying 1K paint designed for spot repair or complete respray of commercial vehicles, machines motorcycles and beguy, goods vehicles in clear, over		

S motorcycles and heavy goods vehicles in clear over base system. Can be used in Chamäleon pre-fill cans.

- speedy initial dry
- can be applied electrostatically
- high UV- and weathering resistance

PAINTING PREPARATION PROCESS

Hardener: without hardener Dilution: Chamäleon UNI thinner 322/323, addition 25 - 30 % Spraying viscosity 4 mm DIN (20°C): 18 - 20 s

Substrate pre-treatment:

The substrate must be clean, dry, free from rust and grease. Remove old/loose coatings or primers.

Old 1	K-paint layers	Make sure existing paint layers are completely removed (sand thoroughly or
		apply a paint removal agent)
Old 2	K-paint lavers	Rough up by sanding and degrease with silicone remover

APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!





CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +12 °C and max. air humidity should not exceed 80%.

Application method	Pressure		Nozzle
Gravity spray gun	2.0 - 2.5 bar		1.2 - 1.3 mm
HVLP	2.0 - 2.2 bar		1.2 - 1.3 mm
Spraying operations	DFT		Consumption
2 - 4	30 - 40 µm		9 - 12 m²/l
Flash-off time	Between the coatings		Before the oven drying
	3 - 5 min		10 - 15 min
Drying	Dust free	Set to touch	Full hardness
Object temperature 20 °C	10 - 15 min	20 - 25 min	1 - 2 h
Object temperature 60 °C			30 min

Shelf life:

36 months, if stored in tightly closed original containers.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.