



CHAM'ALEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAM'ALEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

TECHNICAL DATA SHEET

AEROSOL UNDERBODY PROTECTION

Article number:	37014 (White), 37024 (Grey), 37034 (Black)
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality sprayable preservative against chippings to treat the underside and visible parts of the motor vehicles.
Product characteristics:	<ul style="list-style-type: none">▪ Re-sprayable with all lacquer systems▪ Remains flexible▪ Very good adhesion▪ Resistant to weather influences▪ Resistant to weak acids and bases▪ Excellent corrosion prevention▪ Sound-absorbing
Technical characteristics:	
Contents:	500 ml
VOC-content:	Approximately 74% w/w
Dust dry:	After approximately 30 minutes
Tack free:	After approximately 60 minutes
Re-sprayable:	After 2 hours
Usage:	
	Before use, carefully read the directions on the packaging and act accordingly.
Pre Treatment:	Remove loose old lacquer and rust and sand the surface.
Treatment:	The surface should be clean, dry and free of grease. The aerosol should have room



CHAMALEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMALEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the Chamaeleon Aerosol anti gravel coating in several layers. After drying, without sanding, re-sprayable with all lacquer systems.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

After use:

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via:
info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.