

Product information

Chamäleon Underbody protection Bitumen

Site 1 / 2

Version 1 / 1023

Product description

Chamäleon Underbody protection Bitumen is a highly resistant coating for floor pans, wheel houses and so on. It provides a durable protection against corrosion, de-icing salt and stone-chip. Excellent adhesion, shock- and scratch-resistant, long-term flexible film, good sound deadening properties, non-drip application.

Color

black

Hardener

--

Mixing ratio

--

Dilution

Ready to spray

Spraying viscosity 4 mm DIN

--

Application method

| Application method | Pressure | Nozzle |
|----------------------------|----------|--------|
| Brush or special UBS brush | -- | -- |

Processing conditions

Ensure an adequate supply and exhaust air ventilation. Working temperature must be at least +10 °C. Max. air humidity 80 %.

Spraying operations

| Spraying operations | DFT | Consumption |
|---------------------|--------------|-------------------------|
| -- | approx. 3 mm | 1 - 2 m ² /l |

Flash-off time

--

Pot life at 20 °C

--

Product information

Chamäleon Underbody protection Bitumen

Site 2 / 2

Version 1 / 1023

VOC regulation

EU limit value: Category B/e 840 g/l

This product contains max. 840 g/l.

Processing tips

The floor pan must be cleaned thoroughly. It must be dry, free from dust, grease, oil and rust.

Old non-adherent underbody coating must be removed.

Do not apply on engine, transmission, sump, cardan shaft, exhaust pipes, axles, springs, shock absorber, brake cables, grease nipples, etc..